



CHEM-BOND CCC550

Bonding Agent, Sealer, and Primer

PRODUCT DESCRIPTION

Chem-Bond CCC 550 is a latex liquid emulsion with a especially modified Poly Vinyl Acetate (**PVA**) resin developed as a bonding agent for applying new cementitious repair mortars, etc., onto existing concrete.

Chem-Bond CCC 550 conforms to the requirements of latex bonding agent standard ASTM C1059 Type I.

FIELDS OF APPLICATION

Chem-Bond CCC 550 can be used as bonding admixture to mortar or cement formula or used as surface bonding primer on existing area to be patched with cementitious repair mortar compounds. In basic lime mortars, compressive strengths will increase when **Chem-Bond CCC 550** is used as an admixture, especially effective on mortar joints on windowsills.

PRODUCT FEATURES

- * Excellent bonding strength.
- * Compatible with most common cementitious materials, mineral plasters, etc.
- * Long open placing time.
- * Improves workability and compressive strengths.
- * Non-toxic and non-flammable liquid.

PACKAGING

Product

Chem-Bond CCC 550

Packaging

5 gal/pail
18.9 L /pail

TECHNICAL DATA

Form	Liquid
Colour	Milky white
Density Lb/gal (kg /L)	9 (1.08)
Bond Strength to concrete by slant shear Psi (MPa) (ASTM C-1042)	410 (2.8)
Freeze temperature	0 °C
Boiling point	212° F (100 °C)
Freeze harm	Complete
Odor	Mild latex odor
Toxicity	None
Flammability	None

Clean-up	Water
Fumes during treatment	Slight
Environmental Hazards	None

APPLICATION DATA

Surface Preparation:

When used as a contact bonding material, always make sure that the surface is completely clean and free from pounded water. If the existing surface is a hard trowelled concrete, then etching is recommended prior to the application.

Limitations:

Chem-Bond CCC 550 is a temperature sensitive material. Store at temperatures between 36°F and 90°F (2°C and 32°C).

Coverage:

Varies depending on application and conditions of base concrete, etc.... As a primer, 200ft² per gallon (4.9 m² per liter) in brush application.

Application as Bonding Agent:

- * Apply generous amounts of **Chem-Bond CCC 550** with a roller or brush to the existing moist surfaces that are to receive fresh cementitious materials.
- * Allow first coat application to dry.
- * Apply a second application immediately prior to placing cementitious material.
- * Place the cementitious repair mortars, plasters within tack-free time (approx. 10-15 min.).

Application as Admixture/Cement:

- * Mix the cementitious material per standard procedures.
- * While mixing, add 1.1 gal (4.2 lt.) of **Chem-Bond CCC 550** to each 55 gal (25 kg) of type I Portland cement used in the formula

- * Allow at least an additional five minutes of mixing after the addition of **Chem-Bond CCC 550** to ensure complete blending.
- * Apply blended material to the primed substrate as per standard procedures.

Application as Plaster/Admixture/Gunite:

- * Pre-mix a solution containing 12 parts of water to 1 part of **Chem-Bond CCC 550** and blend thoroughly.
- * Mix approximately 200 lb (91 kg). of the plaster material per standard procedures with the solution as pre-mixed above. Adjust amount of plaster materials as required for desired consistency and/or slump.
- * Use mixed material in standard procedure.

Curing:

Curing of mortars, plasters, etc. made of **Chem-Bond CCC 550**, must observe standard concrete curing methods.

CLEANING

Clean application tools and mixing equipment, etc. with water immediately following use.

STORAGE

Indefinite shelf life when stored in cool, dry place in unopened drums.
Agitate or stir the bucket or drum before using.

SAFETY PRECAUTIONS

As with all construction chemical products, adequate precautions and care must be taken during usage and storage. Avoid direct contact with foodstuff, eyes, skin, and mouth. Keep away from children and animals. Any direct contact with skin, eyes, etc. should be washed

thoroughly with clean running water and soap. Use proper safety wear, goggles, and mask, etc.

NOTICE

The information given in this publication is based on present state of our knowledge. Any recommendations and suggestions are made without guarantee since the conditions and procedures are beyond our control. Buyers and users should make their own assessment of our product under their own conditions and for their own requirements.

TECHNICAL ASSISTANCE

Please contact International Chem-Crete Corporation for Technical Personnel.

WARRANTY

LIMITED WARRANTY: International Chem-Crete Inc. warrants that, at the time and place we make shipment, our materials will be of good quality and will conform to our published specifications in force on the date of acceptance of the order.

DISCLAIMER: The information contained herein is included for illustrative purposes only and, to the best of our knowledge, is accurate and reliable. International Chem-Crete Inc. is not under any circumstances liable to connection with the use of information. As International Chem-Crete Inc. has no control over the use to which others may put its products, it is recommended that the products be tested to determine the suitability for specific applications and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner of the design, application and proper installation of each product. Specifier and user shall determine the suitability of the product for specific application and assume all responsibility in connection therewith. AA/0706

Manufactured By:



International Chem-Crete Inc. , 800 Security Row, Richardson , TX 75081, U.S.A
Tel: (972) 671-6477, Fax: (972) 238-0307
contactus@chem-crete.com www.chem-crete.com